

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 November 2002 (07.11.2002)

PCT

(10) International Publication Number
WO 02/088260 A1

BEST AVAILABLE COPY

(51) International Patent Classification⁷: C09D 5/02,
D21H 19/46

(21) International Application Number: PCT/US02/09945

(22) International Filing Date: 20 March 2002 (20.03.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/837,034 18 April 2001 (18.04.2001) US

(71) Applicant (for all designated States except US): **BASF CORPORATION, PLEASE SEE GENERAL APPOINTMENT OF REPRESENTATIVE** [US/US]; Patent Department, 26701 Telegraph Road, Southfield, MI 48034-2442 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ZHAO, Cheng-Le** [CN/US]; 8632 Castebay Drive, Charlotte, NC 28277 (US). **DITTRICH, Uwe** [DE/DE]; Slevogtstr. 1, 67125 67125 Dannstadt (DE).

(74) Agents: **SABOURIN, Anne, Gerry et al.**; BASF Corporation, 26701 Telegraph Road, Southfield, MI 48034-2442 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:


— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: USE OF SURFACTANTS FOR IMPROVING THE COMPATIBILITY OF INORGANIC PIGMENTS IN AQUEOUS COATING COMPOSITIONS



surfactant. The aqueous composition further includes at least one latex polymer, at least one inorganic pigment and water.

(57) Abstract: The present invention is an aqueous coating composition and method of preparing same that uses certain polyoxyalkylene phosphate surfactants to increase the compatibility of inorganic pigments such as TiO₂ with latex polymer binders to reduce the clustering of the inorganic pigment particles in the aqueous coating composition. The aqueous coating composition of the invention includes at least one polyoxyalkylene phosphate

WO 02/088260 A1

USE OF SURFACTANTS FOR IMPROVING THE COMPATIBILITY OF INORGANIC PIGMENTS IN AQUEOUS COATING COMPOSITIONS

5

Field of the Invention

The present invention relates to the use of surfactants for improving the compatibility of inorganic pigments such as titanium dioxide in aqueous coating compositions such as paint and paper coating compositions. In particular, the present invention related to the use of certain alkoxyated phosphorous-based surfactants for improving the compatibility of inorganic pigments and latex binders in aqueous paint and paper coating compositions.

Background of the Invention

Because of its unique ability to provide maximum light scattering with virtually no light absorption, titanium dioxide (TiO_2) is widely used as a pigment to achieve high opacity (or hiding power) and brightness in white and colored paints, and in other coating compositions. Historically, TiO_2 was produced and used as a dry powder. However, there are a number of problems associated with using TiO_2 powder in the manufacture of coating compositions. In particular, the use of TiO_2 powder can result in dusting and spillage, both of which not only result in pigment loss but also in an unhealthy work environment. Furthermore, the handling of the standard 25-kg bags of TiO_2 powder can lead to extensive exposure to forklift and hand truck hazards, back-related injuries, and other job-related injury risks.

In addition to these problems, TiO_2 powders typically must be ground to be used in coating compositions such as paint compositions. This grinding step is highly power intensive. Moreover, the grinding step can be very time-consuming thereby decreasing the rate at which the TiO_2 powders can be used.

As an alternative to TiO_2 powders, TiO_2 slurries were first introduced to the paper industry in the late 1960's and to the paint industry in the early 1970's. TiO_2 slurries are usually high solids content, e.g., from 60 to 80% by weight, aqueous dispersions of TiO_2 that are stable over a long period of time.

To minimize the settling and aggregation of TiO_2 particles in slurries, dispersants are often used in TiO_2 slurries. The conventional dispersants used in TiO_2 slurries include organic polyelectrolytes, 2-amino-2-methyl-1-propanol, triethanolamine, and


sodium salts of polymeric carboxylic acids. In addition to dispersants, biocides are also used in TiO₂ slurries to preserve the slurries.

The introduction of TiO₂ slurries overcame many of the problems associated with the use of TiO₂ powders and particularly the power intensive and time-consuming step of grinding the TiO₂ powders. Therefore, the use of a TiO₂ slurry results in a significant increase in productivity over the use of TiO₂ powders. Nevertheless, despite the significant advantages of using TiO₂ slurries in aqueous coating compositions such as paper and latex paint compositions, performance deficiencies do exist when using TiO₂ slurries compared with TiO₂ powders. Specifically, it is known, for example, that TiO₂ slurries are often incompatible with the latex binder used in the aqueous coating composition. This problem manifests itself in the form of TiO₂ particle clustering in the paint, which reduces the light scattering efficiency of the pigment, or in the form of lower gloss due to the presence of an incompatible dispersant in the slurry.

Therefore, there is a need in the art to improve the compatibility of TiO₂ slurries and latex binders to limit the clustering of TiO₂ particles and the reduction of gloss in aqueous coating compositions. Moreover, there is a need in the art to improve the compatibility of other inorganic pigments in aqueous compositions.

Summary of the Invention

It has been found that the use of certain polyoxyalkylene phosphate surfactants in aqueous coating compositions limits the clustering of TiO₂ particles in these coating compositions, particularly TiO₂ particles added to the compositions in slurry form. In particular, the aqueous coating composition of the invention includes at least one polyoxyalkylene phosphate surfactant having the following structure:



wherein m is 1 or 2, n is an integer from 1 to 100, R¹ is C1-C5 alkyl, O-R² is an alkylphenol residue wherein R² has the structure C₆H₄-C_pH_{2p+1} or O-R² is a linear or branched alkyl alcohol residue wherein R² has the structure C_pH_{2p+1}, and p is an integer from 1 to 30. The aqueous composition further includes at least one latex polymer, at least one inorganic pigment and water.

In a preferred embodiment of the invention, the surfactant includes a polyoxyethylene phosphate surfactant, i.e., R^1 is ethyl. Moreover, preferably n is from 2 to 30 and more preferably from 3 to 15. For R^2 , p is preferably an integer from 8 to 18 and, in a particularly preferred embodiment, R^2 is nonylphenyl or tridecyl. The at least one inorganic pigment is preferably selected from the group consisting of TiO_2 and $CaCO_3$. The at least one latex polymer is preferably selected from the group consisting of pure acrylics, styrene acrylics, vinyl acrylics and acrylated ethylene vinyl acetate copolymers and more preferably includes a pure acrylic such as a butyl acrylate/methyl methacrylate copolymer. The surfactant discussed above can be incorporated in the latex by using it to produce the latex or it can be added separate from the latex to the aqueous coating composition. The aqueous coating composition can further include at least one anti-freezing agent and one or more additives selected from the group consisting of plasticizers, drying retarders, dispersants, surfactants or wetting agents, rheology modifiers, defoamers, thickeners, coalescing agents, biocides, mildewcides, colorants, waxes, perfumes and co-solvents.

In one preferred embodiment of the invention, the aqueous coating composition is an acrylic latex paint composition, comprising at least one polyoxyalkylene phosphate surfactant as described above; at least one acrylic latex polymer derived from at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters; titanium dioxide and water. For example, the at least one acrylic latex polymer can be selected from the group consisting of pure acrylics, styrene acrylics, vinyl acrylics and acrylated ethylene vinyl acetate copolymers and is more preferably a pure acrylic.

The present invention further includes a method of preparing an aqueous coating composition. Specifically, at least one polyoxyalkylene phosphate surfactant as described above, at least one latex polymer, and at least one inorganic pigment are mixed to produce the aqueous coating composition. Preferably, the at least one inorganic pigment is in slurry form. The at least one inorganic pigment is preferably selected from the group consisting of TiO_2 and $CaCO_3$. The at least one latex polymer is preferably selected from the group consisting of pure acrylics, styrene acrylics, vinyl acrylics and acrylated ethylene vinyl acetate copolymers, and more preferably includes a pure acrylic. At least one anti-freezing agent and at least one additive selected from the group consisting of plasticizers, drying retarders, dispersants, surfactants or wetting agents,

rheology modifiers, defoamers, thickeners, coalescing agents, biocides, mildewcides, colorants, waxes, perfumes and co-solvents, can also be mixed in the composition.

The method can further include the step of preparing the polymer latex binder using emulsion polymerization by feeding monomers to a reactor in the presence of at least one initiator and the at least one surfactant described above and polymerizing the monomers to produce the latex binder. The resulting latex binder can then be mixed with the at least one inorganic pigment to produce the aqueous coating composition. The step of preparing the polymer latex binder can include the steps of preparing an initiator solution comprising the initiator, preparing a monomer pre-emulsion comprising monomers and the surfactant, adding the initiator solution to a reactor and adding the monomer pre-emulsion to the reactor. Preferably, at least a portion of the initiator solution is added to the reactor prior to adding the monomer pre-emulsion. In addition, a seed latex is preferably added to the reactor prior to adding the initiator and adding the monomer pre-emulsion. Once the polymer latex binder is prepared, the latex binder is preferably chemically stripped by adding a peroxide and a reducing agent to the latex binder thereby decreasing the residual monomer content of the latex binder. The monomers fed to a reactor to prepare the polymer latex binder preferably include at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters. In addition, the monomers can include one or more monomers selected from the group consisting of styrene, α -methyl styrene, vinyl chloride, acrylonitrile, methacrylonitrile, ureido methacrylate, vinyl acetate, itaconic acid, crotonic acid, maleic acid, fumaric acid, ethylene, and C4-C8 conjugated dienes such as 1,3-butadiene, isoprene or chloroprene. Preferably, the monomers include one or more monomers selected from the group consisting of n-butyl acrylate, methyl methacrylate, styrene and 2-ethylhexyl acrylate.

By adding the surfactants discussed above, there is little or no clustering of the TiO_2 particles or other inorganic pigment particles in the aqueous coating compositions of the invention as evidenced, e.g., by cryogenic scanning electron micrograph (SEM) analysis. Therefore, the aqueous coating composition maintains better dispersion of the TiO_2 particles or other inorganic pigment particles than conventional compositions that do not use the surfactants of the invention. Semi gloss paint formulations prepared in accordance with the invention also have excellent high shear viscosities, low shear

viscosities, gloss and hiding power and show improvements in these properties over conventional formulations.

These and other features and advantages of the present invention will become more readily apparent to those skilled in the art upon consideration of the following detailed description and accompanying figures, which describe both the preferred and alternative embodiments of the present invention.

Brief Description of the Drawings

Figure 1 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Example 1.

Figure 2 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Example 2.

Figure 3 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Example 3.

Figure 4 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Example 4.

Figure 5 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Example 5.

Figure 6 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Example 6.

Figure 7 is a cryogenic SEM of a semi gloss paint formulation prepared using the latex prepared according to Comparative Example 1.


Detailed Description of the Preferred Embodiments

In the following detailed description, preferred embodiments are described in detail to enable practice of the invention. Although the invention is described with reference to these specific preferred embodiments, it will be understood that the invention is not limited to these preferred embodiments. But to the contrary, the invention includes numerous alternatives, modifications and equivalents as will become apparent from consideration of the following detailed description and accompanying figures.

The present invention is a aqueous coating composition that provides excellent dispersion of TiO₂ particles and other inorganic pigment particles. The aqueous coating

composition of the invention includes at least one particular polyoxyalkylene phosphate surfactant, at least one latex polymer, at least one inorganic pigment and water.


The polyoxyalkylene phosphate surfactant of the invention has the structure:



- 5 wherein m is 1 or 2, n is an integer from 1 to 100, R^1 is C1-C5 alkyl, $\text{O}-\text{R}^2$ is an alkylphenol residue wherein R^2 has the structure $\text{C}_6\text{H}_4-\text{C}_p\text{H}_{2p+1}$ or $\text{O}-\text{R}^2$ is a linear or branched alkyl alcohol residue wherein R^2 has the structure $\text{C}_p\text{H}_{2p+1}$, and p is an integer from 1 to 30. R^1 is typically ethyl, propyl, or a combination thereof, and is more preferably ethyl to produce an ethoxylated phosphate surfactant. In the formula above, m
- 10 is 1 or 2 and typically the surfactants of the invention include a combination of molecules where m is 1 and molecules where m is 2. Further, in the formula above, n is preferably from 2 to 30 and more preferably from 3 to 15. $\text{C}_p\text{H}_{2p+1}$ can be a linear or branched alkyl group and p is preferably an integer from 8 to 18.

In a particularly preferred embodiment, R^2 is nonylphenyl or tridecyl.

- 15 Accordingly, the polyoxyethylene phosphate surfactant preferably has the structure:



- wherein m is 1 or 2, n is an integer from 2 to 30, and R is nonylphenol or tridecyl. Suitable surfactants for use in the invention include DEXTROL® OC-110, DEXTROL® OC-15, DEXTROL® OC-22, DEXTROL® OC-40, DEXTROL® OC-60 and
- 20 DEXTROL® OC-75A, commercially available from Dexter Chemical L.L.C, and POLYSTEP® P-31, POLYSTEP® P-32, POLYSTEP® P-33 and POLYSTEP® P-34, commercially available from Stepan Company. The surfactant is typically present in the aqueous coating composition in an amount from greater than 0 to about 4% by weight based on polymer weight, more preferably from about 0.1 to about 2% by weight based
- 25 on polymer weight.

As mentioned above, the aqueous coating composition includes at least one inorganic pigment. The term "inorganic pigment" as used herein includes non-film-forming solids such as inorganic pigments, extenders, and fillers. The at least one

inorganic pigment is preferably selected from the group consisting of TiO_2 (in both anatase and rutile forms), clay (aluminum silicate), CaCO_3 (in both ground and precipitated forms), talc (magnesium silicate), barytes (barium sulfate), zinc oxide, zinc sulfite, and the like. More preferably, the inorganic pigment includes TiO_2 and/or CaCO_3 . Generally, the mean particle sizes of the inorganic pigments range from about 0.01 to about 50 microns. For example, the TiO_2 particles used in the aqueous coating composition (e.g. provided by the slurry) typically have a mean particle size of from about 0.15 to about 0.40 microns. The inorganic pigment (e.g. TiO_2 and/or CaCO_3) is preferably added to the aqueous coating composition in slurry form. Exemplary TiO_2 slurries for use in the invention include TI-PURE® R-746 and R-942, commercially available from DuPont; TIOXIDE® RCS-535, RCS-9 and R-HD6X, commercially available from Huntsman Corp.; and KRONOS® 4102, commercially available from Kronos, Inc. The inorganic pigment is preferably present in the aqueous coating composition in an amount from about 5 to about 40 percent by weight, more preferably from about 10 to about 30 percent by weight (based on the weight of the inorganic pigment, not the weight of the slurry).

The at least one latex polymer used in the aqueous coating composition is preferably derived from monomers comprising at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters. In addition, the latex polymer can optionally include one or more monomers selected from the group consisting of styrene, α -methyl styrene, vinyl chloride, acrylonitrile, methacrylonitrile, ureido methacrylate, vinyl acetate, itaconic acid, crotonic acid, maleic acid, fumaric acid, and ethylene. It is also possible to include C4-C8 conjugated dienes such as 1,3-butadiene, isoprene and chloroprene. Preferably, the monomers include one or more monomers selected from the group consisting of n-butyl acrylate, methyl methacrylate, styrene and 2-ethylhexyl acrylate. The latex polymer is typically selected from the group consisting of pure acrylics (comprising acrylic acid, methacrylic acid, an acrylate ester, and/or a methacrylate ester as the main monomers), styrene acrylics (comprising styrene and acrylic acid, methacrylic acid, an acrylate ester, and/or a methacrylate ester as the main monomers), vinyl acrylics (comprising vinyl acetate and acrylic acid, methacrylic acid, an acrylate ester, and/or a methacrylate ester as the main monomers) and acrylated ethylene vinyl acetate copolymers (comprising ethylene, vinyl acetate and acrylic acid, methacrylic acid, an acrylate ester, and/or a

methacrylate ester as the main monomers). The monomers can also include other main monomers such as acrylamide and acrylonitrile, and one or more functional monomers such as itaconic acid and ureido methacrylate, as would be readily understood by those skilled in the art. In a particularly preferred embodiment, the latex polymer is a pure acrylic such as a butyl acrylate/methyl methacrylate copolymer derived from monomers including butyl acrylate and methyl methacrylate. The latex polymer dispersion preferably includes from about 30 to about 75% solids and a mean latex particle size of from about 70 to about 650 nm. The latex polymer is preferably present in the aqueous coating composition in an amount from about 5 to about 60 percent by weight, and more preferably from about 8 to about 40 percent by weight (based on the weight of the latex polymer and not the latex dispersion).

The aqueous coating composition can optionally further include at least one anti-freezing agent to improve the freeze-thaw stability of the composition such as propylene glycol, ethylene glycol and diethylene glycol. More preferably, propylene glycol is used. The anti-freezing agent is typically present in the aqueous coating composition in an amount of from 0 to about 15% by weight, more preferably from about 1 to about 10% by weight, based on the total weight of the aqueous coating composition.

The coating composition can optionally contain additives such as one or more film-forming aids. Suitable film-forming aids include plasticizers and drying retarders such as high boiling point polar solvents. Other conventional coating additives such as, for example, dispersants, additional surfactants or wetting agents, rheology modifiers, defoamers, thickeners, coalescing agents, biocides, mildewcides, colorants such as colored pigments and dyes, waxes, perfumes, co-solvents, and the like, can also be used in accordance with the invention. These additives are typically present in the aqueous coating composition in an amount from 0 to about 15% by weight, more preferably from about 1 to about 10% by weight.

The balance of the aqueous coating composition of the invention is water. Although much of the water is present in the polymer latex dispersion, in the inorganic pigment slurry, and in other components of the aqueous coating composition, water is generally also added separately to the aqueous coating composition. Typically, the aqueous coating composition includes from about 10% to about 85% by weight and more preferably from about 50% to about 80% by weight water. Stated differently, the total

solids content of the aqueous coating composition is typically from about 15% to about 90%, more preferably, from about 20% to about 50%.

The coating compositions are typically formulated such that the dried coatings comprise at least 10% by volume of dry polymer solids, and additionally 5 to 90% by volume of non-polymeric solids in the form of inorganic pigments. The dried coatings can also include additives such as plasticizers, dispersants, surfactants or wetting agents, rheology modifiers, defoamers, thickeners, biocides, mildewcides, colorants, waxes, and the like, that do not evaporate upon drying of the coating composition.

In one preferred embodiment of the invention, the aqueous coating composition is a latex paint composition comprising at least one polyoxyalkylene phosphate surfactant as described above; at least one latex polymer derived from at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters; titanium dioxide and water. As mentioned above, the at least one latex polymer can be a pure acrylic, a styrene acrylic, a vinyl acrylic or an acrylated ethylene vinyl acetate copolymer.

The present invention further includes a method of preparing a aqueous coating composition by mixing at least one polyoxyalkylene phosphate surfactant as described above, at least one latex polymer, and at least one inorganic pigment. Preferably, the at least one inorganic pigment is in slurry form and the latex polymer is in the form of a latex polymer dispersion. Typically, the surfactant is either used to produce the latex polymer dispersion as discussed below or is mixed with the latex polymer dispersion prior to mixing the inorganic pigment with the surfactant and latex polymer to produce the aqueous coating composition of the invention. Alternatively, the at least one polyoxyalkylene phosphate surfactant described above can be mixed with the at least one inorganic pigment in slurry form and the resultant mixture then mixed with the latex polymer dispersion. The additives discussed above can be added in any suitable order to either the surfactant, the latex polymer, the inorganic pigment, or combinations thereof, to provide these additives in the aqueous coating composition. In the case of paint formulations, the aqueous coating composition preferably has a pH of from 7 to 10.

The phosphate surfactant of the invention can be used to produce the polymer latex binder for the aqueous coating composition. In particular, the polymer latex binder can be prepared using emulsion polymerization by feeding the monomers used to form the latex binder to a reactor in the presence of at least one initiator and the at least one of

the phosphate surfactants of the invention and polymerizing the monomers to produce the latex binder. The monomers fed to a reactor to prepare the polymer latex binder preferably include at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters. In addition, the monomers can include styrene, vinyl acetate, or ethylene. The monomers can also include one or more monomers selected from the group consisting of styrene, α -methyl styrene, vinyl chloride, acrylonitrile, methacrylonitrile, ureido methacrylate, vinyl acetate, itaconic acid, crotonic acid, maleic acid, fumaric acid, and ethylene. It is also possible to include C4-C8 conjugated dienes such as 1,3-butadiene, isoprene or chloroprene. Preferably, the monomers include one or more monomers selected from the group consisting of n-butyl acrylate, methyl methacrylate, styrene and 2-ethylhexyl acrylate. The initiator can be any initiator known in the art for use in emulsion polymerization such as ammonium persulfate.

The polymer latex binder can be produced by first preparing an initiator solution comprising the initiator and water. A monomer pre-emulsion is also prepared comprising at least a portion of the monomers to be used to form the latex polymer, one or more surfactants, water, and additional additives such as NaOH. The one or more surfactants in the monomer pre-emulsion preferably include the surfactant of the invention described above. The initiator solution and monomer pre-emulsion are then continuously added to the reactor over a predetermined period of time (e.g. 2-5 hours) to cause polymerization of the monomers and to thereby produce the latex polymer. Preferably, at least a portion of the initiator solution is added to the reactor prior to adding the monomer pre-emulsion. Prior to the addition of the initiator solution and the monomer pre-emulsion, a seed latex such as a polystyrene seed latex can be added to the reactor. In addition, water, one or more surfactants, and any monomers not provided in the monomer pre-emulsion can be added to the reactor prior to adding the initiator and adding the monomer pre-emulsion. The reactor is operated at an elevated temperature at least until all the monomers are fed to produce the polymer latex binder. Once the polymer latex binder is prepared, it is preferably chemically stripped thereby decreasing its residual monomer content. Preferably, it is chemically stripped by continuously adding a peroxide (e.g. t-butylhydroperoxide) and a reducing agent (e.g. sodium acetone bisulfite) to the latex binder at an elevated temperature and for a predetermined period of time (e.g. 0.5 hours).


The pH of the latex binder can then be adjusted and a biocide or other additives added after the chemical stripping step.

The aqueous coating composition is a stable fluid that can be applied to a wide variety of materials such as, for example, paper, wood, concrete, metal, glass, ceramics, plastics, plaster, and roofing substrates such as asphaltic coatings, roofing felts, foamed polyurethane insulation; or to previously painted, primed, undercoated, worn, or weathered substrates. The aqueous coating composition of the invention can be applied to the materials by a variety of techniques well known in the art such as, for example, brush, rollers, mops, air-assisted or airless spray, electrostatic spray, and the like.

The present invention will now be further described by the following non-limiting examples.

EXAMPLE 1 (E1)



Example 1 illustrates the preparation of a polymer dispersion containing 1% (weight percent of active material based on dry polymer weight) DEXTROL® OC-110 (Dexter Chemical L.L.C.). DEXTROL® OC-110 is a mixture of compounds I and II below:



A monomer pre-emulsion was prepared by emulsifying 336.7 parts water, 5.3 parts CALSOFT® L-40 (a sodium linear or branched alkyl benzene sulfonate surfactant commercially available from Pilot Chemical), 10.0 parts DEXTROL® OC-110, 13.3 parts TEXAPON® K1296 (a sodium lauryl sulfate surfactant commercially available from Cognis Corporation), 18 parts NaOH solution (10% solution in water), 5 parts itaconic acid, 25 parts acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl

acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0 parts deionized water, 3.14 parts of a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85°C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4 parts of initiator solution, the monomer pre-emulsion was continuously fed into the reactor over 3.0 hours. At the end of the initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70°C.

To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70°C for 30 minutes before being cooled down to below 40°C. The pH of the latex was adjusted to 8.6 with concentrated ammonia. 100 ppm (parts per million) of ACTICIDE® MV14 (a biocide commercially available from Acti-Chem Specialties, Inc.), based on dry polymer weight, was added to the latex. The resulting polymer dispersion had a solids content of 49.5% and a diameter of 122 nm by



photocorrelation spectroscopy.

EXAMPLE 2 (E2)



Example 2 was prepared according to the same process and using the same ingredients as in Example 1 except that Example 2 contained 1% (weight percent of active material based on dry polymer weight) DEXTROL® OC-15 (Dexter Chemical L.L.C.) instead of DEXTROL® OC-110. DEXTROL® OC-15 is a mixture of
5 compounds III and IV below:

A monomer pre-emulsion was prepared by emulsifying 336.7 parts water, 5.3 parts CALSOFT® L-40, 10.0 parts DEXTROL® OC-15, 13.3 parts TEXAPON®
10 K1296, 18 parts NaOH solution (10% solution in water), 5 parts itaconic acid, 25 parts acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0
15 parts deionized water, 3.14 parts of a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85°C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4 parts of initiator solution, the monomer pre-emulsion was continuously fed into the
20 reactor over 3.0 hours. At the end of the initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70°C.

To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-
25 butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70°C for 30 minutes before being cooled down
30 to below 40°C. The pH of the latex was adjusted to 8.4 with concentrated ammonia. 100 ppm of ACTICIDE® MV14, based on dry polymer weight, was added to the latex. The resulting polymer dispersion had a solids content of 50.9% and a diameter of 125 nm by photocalorrelation spectroscopy.

EXAMPLE 3 (E3)

Example 3 was prepared according to the same process and using the same ingredients as in Example 1 except that Example 3 contained 1% (weight percent of active material based on dry polymer weight) DEXTROL® OC-22 (Dexter Chemical L.L.C.) instead of DEXTROL® OC-110. DEXTROL® OC-22 is a mixture of compounds V and VI below:





A monomer pre-emulsion was prepared by emulsifying 336.7 parts water, 5.3 parts CALSOFT® L-40, 10.0 parts DEXTROL® OC-22, 13.3 parts TEXAPON® K1296, 18 parts NaOH solution (10% solution in water), 5 parts itaconic acid, 25 parts acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0 parts deionized water, 3.14 parts of a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85°C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4 parts of initiator solution, the monomer pre-emulsion was continuously fed into the reactor over 3.0 hours. At the end of the initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70°C.

To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a

reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70°C for 30 minutes before being cooled down to below 40°C. The pH of the latex was adjusted to 8.3 with concentrated ammonia. 100 ppm of ACTICIDE® MV14, based on dry polymer weight, was added to the latex. The resulting polymer dispersion had a solids content of 49.9% and a diameter of 117 nm by photocorrelation spectroscopy.

EXAMPLE 4 (E4)

Example 4 was prepared according to the same process and using the same ingredients as in Example 1 except that Example 4 contained 1% (weight percent of active material based on dry polymer weight) DEXTROL® OC-40 (Dexter Chemical L.L.C.) instead of DEXTROL® OC-110. DEXTROL® OC-40 is a mixture of compounds VII and VIII below:





A monomer pre-emulsion was prepared by emulsifying 336.7 parts water, 5.3 parts CALSOFT® L-40, 10.0 parts DEXTROL® OC-40, 13.3 parts TEXAPON® K1296, 18 parts NaOH solution (10% solution in water), 5 parts itaconic acid, 25 parts acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0 parts deionized water, 3.14 parts of a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85 °C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4

parts of initiator solution, the monomer pre-emulsion was continuously fed into the reactor over 3.0 hours. At the end of the initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70 °C.

- 5 To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing
- 10 agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70 °C for 30 minutes before being cooled down to below 40°C. The pH of the latex was adjusted to 8.5 with concentrated ammonia. 100 ppm of ACTICIDE® MV14, based on dry polymer weight, was added to the latex. The resulting polymer dispersion had a solids content of 50.28% and a diameter of 117 nm by
- 15 photocorrelation spectroscopy.

EXAMPLE 5 (E5)

- Example 5 was prepared according to the same process and using the same ingredients as in Example 1 except that Example 5 contained 1% (weight percent of
- 20 active material based on dry polymer weight) DEXTROL® OC-60 (Dexter Chemical L.L.C.) instead of DEXTROL® OC-110. DEXTROL® OC-60 is a mixture of compounds IX and X below:





- A monomer pre-emulsion was prepared by emulsifying 336.7 parts water, 5.3
- 25 parts CALSOFT® L-40, 10.0 parts DEXTROL® OC-60, 13.3 parts TEXAPON® K1296, 18 parts NaOH solution (10% solution in water), 5 parts itaconic acid, 25 parts

acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0 parts deionized water, 3.14 parts of a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85 °C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4 parts of initiator solution, the monomer pre-emulsion was continuously fed into the reactor over 3.0 hours. At the end of the initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70 °C.

To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70 °C for 30 minutes before being cooled down to below 40°C. The pH of the latex was adjusted to 8.4 with concentrated ammonia. 100 ppm of ACTICIDE® MV14, based on dry polymer weight, was added to the latex. The resulting polymer dispersion had a solids content of 50.40% and a diameter of 115 nm by photocorrelation spectroscopy.

EXAMPLE 6 (E6)

Example 6 was prepared according to the same process and using the same ingredients as in Example 1 except that Example 6 contained 1% (weight percent of active material based on dry polymer weight) DEXTROL® OC-75A (Dexter Chemical L.L.C.) instead of DEXTROL® OC-110. DEXTROL® OC-75A is a mixture of compounds XI and XII below:



A monomer pre-emulsion was prepared by emulsifying 336.7 parts water, 5.3 parts CALSOFT® L-40, 10.0 parts DEXTROL® OC-75A, 13.3 parts TEXAPON® K1296, 18 parts NaOH solution (10% solution in water), 5 parts itaconic acid, 25 parts acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0 parts deionized water, 3.14 parts of a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85 °C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4 parts of initiator solution, the monomer pre-emulsion was continuously fed into the reactor over 3.0 hours. At the end of the initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70 °C.

To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70 °C for 30 minutes before being cooled down to below 40°C. The pH of the latex was adjusted to 8.3 with concentrated ammonia. 100 ppm of ACTICIDE® MV14, based on dry polymer weight, was added to the latex. The resulting polymer dispersion had a solids content of 46.56% and a diameter of 117 nm by photocalorrelation spectroscopy.

COMPARATIVE EXAMPLE 1 (CE1)

Comparative Example 1 was prepared according to the same process and using the same ingredients as in Example 1, except that Comparative Example 1 contained no
5 DEXTROL® surfactants. Comparative Example 1 contained 0.5% of CALSOFT® L-40S versus 0.2% in E1 through E3 (weight percent of active material based on dry polymer weight).

A monomer pre-emulsion was prepared by emulsifying 331.8 parts water, 13.2 parts CALSOFT® L-40, 13.3 parts TEXAPON® K1296, 18 parts NaOH solution (10%
10 solution in water), 5 parts itaconic acid, 25 parts acrylamide solution (50% in water), 5 parts acrylic acid, 48 parts ureido methacrylate solution (25% solution in methyl methacrylate), 460 parts n-butyl acrylate and 464.5 parts methyl methacrylate. The initiator solution was prepared by dissolving 2.0 parts ammonium persulfate in 38.0 parts water. A 2-liter stirred glass reactor filled with 498.0 parts deionized water, 3.14 parts of
15 a 33% polystyrene seed latex and 5.0 parts itaconic acid, was purged with nitrogen and heated to 85°C. When the temperature was reached, 4 parts of the initiator solution was injected into the reactor and the remaining initiator solution was continuously fed into the reactor over 3.1 hours. After the charge of the 4 parts of initiator solution, the monomer pre-emulsion was continuously fed into the reactor over 3.0 hours. At the end of the
20 initiator feed, 4.4 parts concentrated ammonia (25% in water) was added into the reactor. The reaction was further allowed to continue for 30 minutes before being cooled down to 70°C.

To further reduce the residual monomer level, a chemical stripping step was conducted. A peroxide solution was prepared consisting of 1.43 parts of t-
25 butylhydroperoxide solution (tBHP, 70% in water) and 25.2 parts water. In addition, a reducing agent solution was prepared consisting of 6.7 parts of sodium acetone bisulfite solution (SABS solution, 24% in water) and 19.9 parts water. The peroxide and reducing agent solutions were fed separately and continuously to the reactor over 0.5 hours. After both feeds, the reactor was maintained at 70°C for 30 minutes before being cooled down
30 to below 40°C. The pH of the latex was adjusted to 8.4 with concentrated ammonia. 100 ppm of ACTICIDE® MV14, based on dry polymer weight, was added to the latex. The resulted polymer dispersion has a solid content of 50.3% and a diameter of 122 nm by photocorrelation spectroscopy.

PAINT FORMULATION

The following semi gloss, TiO₂ slurry-based paint formulation was used for evaluating the paint performances and the state of dispersion of TiO₂ particles in paints prepared using the latices of Examples 1-6 and Comparative Example 1.

<u>Ingredients</u>	<u>Parts by Weight</u>
Water	64.0
Propylene Glycol	65.0
2-Amino-2-Methyl-Propanol (AMP-95)	2.0
TAMOL® 731 ¹	5.0
FOAMASTER® VL ²	1.0
PROXEL® GXL ³	3.0
TiO ₂ Slurry (TI-PURE® R-746 ⁴)	350.3

The above components were mixed at 1000 rpm for 20 minutes and then the following components were added to the mixer:

Latex (50%)	490.0
TEXANOL® ⁵	24.5
FOAMASTER® VL	1.0
ACRYSOL® RM 2020 ⁶	28.4
Water	47.0

¹ TAMOL® 731 is a dispersant based on a sodium salt of a hydrophobic copolymer commercially available from Rohm and Haas.

² FOAMASTER® VL is a defoamer based on a proprietary blend of esters, oils, and silica derivatives commercially available from Henkel Corporation.

³ PROXEL® GXL is a biocide based on 1,2-benzisothiazolin-3-one commercially available from Zeneca.

⁴ TI-PURE® R-746 is a TiO₂ slurry with 76.5% solids content commercially available from DuPont.

⁵ TEXANOL® is a 2,2,4-trimethyl-1,3-pentanediol mono(2-methylpropanoate) coalescing agent commercially available from Eastman Chemicals.

⁶ ACRYSOL® RM 2020 is a hydrophobically modified ethoxylated urethane block copolymer for adjusting high-shear viscosity (ICI) commercially available from Rohm and Haas.

TEST METHODS

Stormer Viscosity (in KU, Krebs Units): The Stormer viscosity was measured according to ASTM D 562-81.

5 **ICI Viscosity** (in Poise): The high shear ICI viscosity was measured according to ASTM D 4287-94.

Freeze-Thaw Stability: The high freeze-thaw stability of the paints was tested according to ASTM D 2243. The freezer temperature was set at -18°C. Stormer viscosities were measured after each freeze-thaw cycle, if the paint did not coagulate.

10 **Draw-Down of Films:** After the third freeze-thaw cycle, a draw-down of the paint was made on white sealed paper (Plain Leneta white paper chart) with a 7 MILS (180 μm thickness) blade. A pass or failure note was given based on the grit level in the dried paint film. A paint film with sporadic microcoagulum was rated a "pass" and a paint film with a large amount of coagulum was rated a "fail". The rating gives information on freeze-thaw stability of the paint to supplement the stormer viscosity measurement.

20 **Gloss:** Gloss measurement was carried out based on ASTM D 523. Wet paints of 3 MILS thickness (75 μm) were drawn on Leneta PVC scrub panels and allowed to dry in a climate-controlled room (22°C and 50% RH) for 72 hours. At least three readings were taken in various locations. Gloss values of 20° and 60° geometries were recorded for the semi gloss paints.

25 **Contrast Ratio:** Contrast Ratio was measured based on ASTM D 2805-96a. Wet paints of 3 MILS thickness (75 μm) were drawn on Leneta Opacity charts and allowed to dry in a climate-controlled room (22°C and 50% RH) for 72 hours. At least three readings of reflectance were taken in different locations of the test area and mean values were calculated. The contrast ratio is the ratio of the reflectance of a paint film on a black area to that of an identical film on a white area.

PAINT TEST RESULTS

30 The test results of the semi gloss paints based on the latices from Examples 1-6 and Comparative Example 1 are summarized in Table 1.

TABLE 1

	Paint #1 Based on E1	Paint #2 Based on E2	Paint #3 Based on E3	Paint #4 Based on E4	Paint #5 Based on E5	Paint #6 Based on E6	Paint #7 Based on CE1
Stormer Viscosity (KU)	87	84	83	84	79	86	82
ICI Viscosity (poise)	1.44	1.39	1.48	1.42	1.38	1.59	1.18
Freeze-Thaw Stability (KU after 1,2,3,4,5 cycles)	86/90/88/93/92	86/89/86/91/90	86/88/88/89/90	86/88/86/88/86	82/85/82/84/83	88/89/88/90/87	86/89/87/88/87
Grit in Draw Down Films after 3 Freeze- Thaw Cycles	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Gloss @ 20°/60°	27/74	22/72	27/75	29/77	22/71	28/74	10/55
Contrast Ratio	97.9	97.4	98.3	98.9	97.1	98.3	96.4

The test results in Table 1 show that the semi gloss paints based on the polymer latices of Examples 1-6 have higher high-shear (ICI) viscosities, higher gloss and higher contrast ratios (higher hiding power) than the control paint based on the latex of the Comparative Example 1 as is desirable in paint formulations. Furthermore, the semi gloss paints based on the polymer latices of Examples 1-6 have low-shear (Stormer) viscosities that are comparable to the low-shear viscosity for the paint based on the latex of Comparative Example 1.


The cryogenic SEM pictures of the paints are provided in Figures 1-7. Figures 1-6, which correspond to the semi gloss paints based on the polymer latices of Examples 1-6, respectively, show that the semi gloss paints based on the polymer latices of Examples 1-6 have improved dispersion of the TiO_2 particles than the semi gloss paint based on the polymer latex of Comparative Example 1 illustrated in Figure 7, which contains clusters of TiO_2 particles. As the results in Table 1 demonstrate, the semi gloss paints based on Examples 1-6 not only exhibit better TiO_2 dispersion but also exhibit improved performance over the semi gloss paint based on Comparative Example 1.

It is understood that upon reading the above description of the present invention, one skilled in the art could make changes and variations therefrom. These changes and variations are included in the spirit and scope of the following appended claims.

THAT WHICH IS CLAIMED:

1. A aqueous coating composition, comprising:

(a) at least one polyoxyalkylene phosphate surfactant having the following structure:



wherein m is 1 or 2, n is an integer from 1 to 100, R¹ is C1-C5 alkyl, O-R² is an alkylphenol residue wherein R² has the structure C₆H₄-C_pH_{2p+1} or O-R² is a linear or branched alkyl alcohol residue wherein R² has the structure C_pH_{2p+1}, and p is an integer from 1 to 30;

- (b) at least one latex polymer;
 (c) at least one inorganic pigment; and
 (d) water.


2. The composition according to Claim 1, wherein R¹ is ethyl.

3. The composition according to Claim 1, wherein n is from 2 to 30.

4. The composition according to Claim 1, wherein n is from 3 to 15.


5. The composition according to Claim 1, wherein p is an integer from 8 to 18.

6. The composition according to Claim 1, wherein the surfactant is a polyoxyethylene surfactant having the following structure:



wherein m is 1 or 2, n is an integer from 2 to 30, and O-R is an alkylphenol residue wherein R has the structure C₆H₄-C_pH_{2p+1} and p is an integer from 8 to 18.

7. The composition according to Claim 1, wherein the surfactant is a polyoxyethylene surfactant having the following structure:



5 wherein m is 1 or 2, n is an integer from 2 to 30, and O-R is an alkyl alcohol residue wherein R has the structure C_pH_{2p+1} and p is an integer from 8 to 18.

8. The composition according to Claim 1, wherein R^2 is nonylphenyl or tridecyl.

10

9. The composition according to Claim 1, wherein the inorganic pigment is selected from the group consisting of TiO_2 , clay, $CaCO_3$, talc, barytes, zinc oxide and zinc sulfite.

15 10. The composition according to Claim 1, wherein the inorganic pigment includes TiO_2 .

11. The composition according to Claim 1, wherein the surfactant is incorporated in the latex.

20

12. The composition according to Claim 1, wherein the at least one latex polymer is selected from the group consisting of pure acrylics, styrene acrylics, vinyl acrylics and acrylated ethylene vinyl acetate copolymers.

25 13. The composition according to Claim 1, wherein the at least one latex polymer includes a pure acrylic.

14. The composition according to Claim 13, wherein the at least one latex polymer is derived from at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters.


30

15. The composition according to Claim 14, wherein the at least one latex polymer is further derived from one or more monomers selected from the group consisting of styrene, α -methyl styrene, vinyl chloride, acrylonitrile, methacrylonitrile, ureido methacrylate, vinyl acetate, itaconic acid, crotonic acid, maleic acid, fumaric acid, ethylene, and C4-C8 conjugated dienes.

16. The composition according to Claim 1, further comprising at least one anti-freezing agent.

17. The composition according to Claim 1, further comprising one or more additives selected from the group consisting of plasticizers, drying retarders, dispersants, surfactants or wetting agents, rheology modifiers, defoamers, thickeners, coalescing agents, biocides, mildewcides, colorants, waxes, perfumes and co-solvents.

18. A latex paint composition, comprising:
(a) at least one polyoxyalkylene phosphate surfactant having the following structure:




wherein m is 1 or 2, n is an integer from 2 to 30, R^1 is ethyl, $\text{O}-\text{R}^2$ is an alkylphenol residue wherein R^2 has the structure $\text{C}_6\text{H}_4-\text{C}_p\text{H}_{2p+1}$ or $\text{O}-\text{R}^2$ is a linear or branched alkyl alcohol residue wherein R^2 has the structure $\text{C}_p\text{H}_{2p+1}$, and p is an integer from 8 to 18;

(b) at least one latex polymer derived from at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters;

(c) titanium dioxide; and


(d) water.

19. The paint composition according to Claim 18, wherein said mixing step comprises mixing at least one surfactant having the following structure:



where m is 1 or 2, n is an integer from 2 to 30, and O-R is an alkylphenol residue wherein R has the structure $\text{C}_6\text{H}_4-\text{C}_p\text{H}_{2p+1}$ and p is an integer from 8 to 18.

- 5 20. The paint composition according to Claim 18, wherein said mixing step comprises mixing at least one surfactant having the following structure:



where m is 1 or 2, n is an integer from 2 to 30, and O-R is an alkyl alcohol residue wherein R has the structure $\text{C}_p\text{H}_{2p+1}$ and p is an integer from 8 to 18.

10


21. The paint composition according to Claim 18, wherein said mixing step comprises mixing at least one surfactant wherein R^2 is nonylphenyl or tridecyl.

22. The paint composition according to Claim 18, wherein the latex polymer
15 is a pure acrylic latex polymer.

23. The paint composition according to Claim 22, wherein the latex polymer is a butyl acrylate/methyl methacrylate copolymer.

- 20 24. A method of preparing a aqueous coating composition, comprising the step of:

mixing at least one polyoxyalkylene phosphate surfactant having the following structure:



wherein m is 1 or 2, n is an integer from 1 to 100, R¹ is C1-C5 alkyl, O-R² is an alkylphenol residue wherein R² has the structure C₆H₄-C_pH_{2p+1} or O-R² is a linear or branched alkyl alcohol residue wherein R² has the structure C_pH_{2p+1}, and p is an integer from 1 to 30; at least one latex polymer; and at least one inorganic pigment.

5

25. The method according to Claim 24, wherein said mixing step comprises mixing at least one inorganic pigment in slurry form.

26. The method according to Claim 25, wherein said mixing step comprises
10 blending the surfactant with the at least one inorganic pigment in slurry form prior to mixing the surfactant and at least one inorganic pigment with the at least one latex polymer.

27. The method according to Claim 24, wherein said mixing step comprises
15 mixing at least one surfactant wherein R¹ is ethyl.


28. The method according to Claim 24, wherein said mixing step comprises mixing at least one surfactant wherein n is from 2 to 30.

29. The method according to Claim 24, wherein said mixing step comprises
20 mixing at least one surfactant wherein n is from 3 to 15.

30. The method according to Claim 24, wherein said mixing step comprises mixing at least one surfactant wherein p is an integer from 8 to 18.


25

31. The method according to Claim 24, wherein said mixing step comprises mixing at least one surfactant having the following structure:



where m is 1 or 2, n is an integer from 2 to 30, and O-R is an alkylphenol residue wherein R has the structure $C_6H_4-C_pH_{2p+1}$, and p is an integer from 8 to 18.

32. The method according to Claim 24, wherein said mixing step comprises
5 mixing at least one surfactant having the following structure:



where m is 1 or 2, n is an integer from 2 to 30, and O-R is an alkyl alcohol residue wherein R has the structure C_pH_{2p+1} and p is an integer from 8 to 18.

- 10 33. The method according to Claim 24, wherein said mixing step comprises mixing at least one surfactant wherein R^2 is nonylphenyl or tridecyl.

34. The method according to Claim 24, wherein said mixing step comprises mixing at least one inorganic pigment wherein the inorganic pigment is selected from the
15 group consisting of TiO_2 , clay, $CaCO_3$, talc, barytes, zinc oxide and zinc sulfite.

35. The method according to Claim 24, wherein the inorganic pigment includes TiO_2 .

- 20 36. The method according to Claim 24, wherein said mixing step comprises mixing at least one latex polymer selected from the group consisting of pure acrylics, styrene acrylics, vinyl acrylics and acrylated ethylene vinyl acetate copolymers.

37. The method according to Claim 24, wherein the at least one latex polymer
25 includes a pure acrylic.

38. The method according to Claim 24, wherein the at least one latex polymer is derived from at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters.

30

39. The method according to Claim 38, wherein the at least one latex polymer is further derived from one or more monomers selected from the group consisting of styrene, α -methyl styrene, vinyl chloride, acrylonitrile, methacrylonitrile, ureido methacrylate, vinyl acetate, itaconic acid, crotonic acid, maleic acid, fumaric acid, ethylene, and C4-C8 conjugated dienes.

40. The method according to Claim 24, wherein said mixing step comprises further mixing at least one anti-freezing agent.

41. The method according to Claim 24, wherein said mixing step comprises further mixing at least one additive selected from the group consisting of plasticizers, drying retarders, dispersants, surfactants or wetting agents, rheology modifiers, defoamers, thickeners, coalescing agents, biocides, mildewcides, colorants, waxes, perfumes and co-solvents.

42. The method according to Claim 24, further comprising the step of preparing the polymer latex binder using emulsion polymerization by feeding monomers to a reactor in the presence of at least one initiator and the at least one surfactant and polymerizing the monomers to produce the latex binder, wherein said mixing step comprises mixing the at least one inorganic pigment with the resulting latex binder to prepare the aqueous coating composition.

43. The method according to Claim 42, wherein said step of preparing the polymer latex binder comprises:

- preparing an initiator solution comprising the initiator;
- preparing a monomer pre-emulsion comprising monomers and the surfactant;
- adding the initiator solution to a reactor; and
- adding the monomer pre-emulsion to the reactor.

44. The method according to Claim 43, wherein at least a portion of said initiator solution is added to the reactor prior to adding the monomer pre-emulsion.

45. The method according to Claim 43, further comprising the step of adding a seed latex to the reactor prior to adding the initiator and adding the monomer pre-emulsion.


5 46. The method according to Claim 43, further comprising the step of chemically stripping the latex binder by adding a peroxide and a reducing agent to the latex binder thereby decreasing the residual monomer content of the latex binder.

47. The method according to Claim 43, wherein said preparing step comprises feeding monomers to a reactor comprising at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters.

48. The method according to Claim 44, wherein said preparing step comprises feeding monomers to a reactor further comprising one or more monomers selected from the group consisting of styrene, α -methyl styrene, vinyl chloride, acrylonitrile, methacrylonitrile, ureido methacrylate, vinyl acetate, itaconic acid, crotonic acid, maleic acid, fumaric acid, ethylene, and C4-C8 conjugated dienes.


49. A method of preparing a aqueous latex paint composition, comprising the step of:

mixing at least one polyoxyethylene phosphate surfactant having the following structure:



where m is 1 or 2, n is an integer from 2 to 30, R^1 is ethyl, $\text{O}-\text{R}^2$ is an alkylphenol residue wherein R^2 has the structure $\text{C}_6\text{H}_4-\text{C}_p\text{H}_{2p+1}$ or $\text{O}-\text{R}^2$ is a linear or branched alkyl alcohol residue wherein R^2 has the structure $\text{C}_p\text{H}_{2p+1}$, and p is an integer from 8 to 18; at least one latex polymer derived from at least one acrylic monomer selected from the group consisting of acrylic acid, acrylic acid esters, methacrylic acids, and methacrylic acid esters; and titanium dioxide in slurry form.

50. In a method for limiting the clustering of TiO_2 particles in a aqueous coating composition comprising a polymer latex and water, the improvement comprising adding at least one polyoxyalkylene phosphate surfactant having the following structure:



wherein m is 1 or 2, n is an integer from 1 to 100, R^1 is C1-C5 alkyl, $O-R^2$ is an alkylphenol residue wherein R^2 has the structure $-C_6H_4-C_pH_{2p+1}$ or $O-R^2$ is a linear or branched alkyl alcohol residue wherein R^2 has the structure $-C_pH_{2p+1}$ and p is an integer from 1 to 30, to the aqueous coating composition.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/09945

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09D5/02 D21H19/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D D21H B01F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 99 46337 A (BASF AG ; DERSCH ROLF (DE); ZHAO CHENG LE (DE); LEY GREGOR (DE); HA) 16 September 1999 (1999-09-16) page 2, line 28 -page 3, line 39 page 9, line 22 -page 10, line 10 page 10, line 25-45	1, 11, 12, 18, 24, 49
A	US 4 927 463 A (KLOETZER ERHARD ET AL) 22 May 1990 (1990-05-22) column 3, line 10-44	1, 18, 24

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

30 July 2002

Date of mailing of the international search report

07/08/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Miller, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/09945

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9946337	A	16-09-1999	DE 19810658 A1	25-11-1999
			AU 3031099 A	27-09-1999
			WO 9946337 A1	16-09-1999
			EP 1062282 A1	27-12-2000
			JP 2002506111 T	26-02-2002
			US 6348528 B1	19-02-2002
<hr/>				
US 4927463	A	22-05-1990	DE 3811763 A1	09-11-1989
			AT 83017 T	15-12-1992
			DE 58902849 D1	14-01-1993
			EP 0339310 A1	02-11-1989
			ES 2037310 T3	16-06-1993
<hr/>				

THIS PAGE BLANK (USPTO)

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)